

POLYAIR

4mm Polyethylene with Rigid Bubble Core
Satin Finish

Common Uses
Parties, Events, Presentations & More

Environment
Indoor & Outdoor

Print Sides
Single-sided
Double-sided

Size Options
Custom Size

Technical Data >

TECHNICAL DATA SHEET

PROPERTIES

Polypropylene (9003-07-0): 95-100%
Polypropylene Copolymer (9010-79-1): 95-100%

RIGID BUBBLE CORE

Board Weight (Primex): 120g/sqft
Board Weight (Primex): 260lbs/MSF
Tensile Strength (ASTM D638): 830psi
Tensile Modulus (ASTM D638): 24,000psi
Flexural Modulus (ASTM D790): 84,000psi
Compression Strength (Primex): 175lbf
90° Corner Crush (Primex): 270lbf

IDX TEXAS

www.idxde.com | 903-660-9094 | engraveus@idxtx.com
IDX DESIGN & ENGRAVING | FLINT, TX